



## Exotic-Wood-Oil

**For exotic and common timbers exterior, natural-toned  
e.g. wooden-terrace floors, carports, wood-decks, outdoor furniture**

### Basic:

Upgraded natural oils, e.g. sunflower-, soy-, swiss-stone-pineal-, thistle- and rapeseed oil, tree-resins, cobalt- and calcium soaps, de-aromatic hydrocarbons, iron-oxid pigments

### Use and Characteristic:

IRSA Exotic-Wood-Oil is protecting exotic woodworks (e.g. bankirai, iroko, mahogany, meranti, nyatoh, robbie, jarrah, belinga) also appropriate for douglas fir, robinia, oak, larch, and cedar.

IRSA Exotic-Wood-Oil contains resistant, weather-proofed oils and micro-fine pigments. UV-rays become effectively blocked and protected effectively against damage. (Nearly preventing cracks-forming by swelling and shrinking of wood). Enhancing the natural colour of wood, low wooden tone deflection.

IRSA Exotic-Wood-Oil is free of toxic substances, biodegradable and scentless after drying. The surface remains open-porous, respiration-active and is re-paintable, even only partial- and without intermediate sanding. Generally we recommend to carry out a patch test first.

IRSA Exotic-Wood-Oil is protecting and upgrading high-grade timber exterior, new and for renovation. Versatile use, e.g. terrace-floors, wood-decks, carports, outdoor-furniture, façade boards, window shutters, doors garden sheds, balconies, fences, wooden toys and panel-boards. To protect against blue mould and rot on soft woods, we recommend a pre-treatment with an appropriate impregnating agent.

### Application:

The surface must be dry, absorbing, frost-free, clean and dust-free. Remove grease, dirt, algas, etc. with IRSA AQUA CLEANER 5000. Remove thick-layer-systems and all pore-filling old-paintings by sanding, paint stripping or burning-off.

Shake the IRSA Exotic-Wood-Oil or stir well before use and apply on pure, rough timber 2-3 x (approx. 50ml/m<sup>2</sup>) with intermediate drying times of approx. 12 hours. Use a soft-brush or coated-brush for evenly application. IRSA Exotic-Wood-Oil also can also be applied by spraying or dipping. Dampness of wood not over 12%. Temperature of processing at a minimum of +8°C. Clean the tools, etc. with IRSA Thinner B or soap-water. When working with several couples and different lot numbers, mix together in a separate container to prevent visible deflections.

For additional maintenance, IRSA Exotic-Wood-Oil also can be applied on all conventional paint layers as far as the underground floor has a load-bearing capacity. Incapacity of foundations need to be sanded first. Processing with the paint layer structure as described. Different effects may appear depending on the surface structure. Carry out a patch test first.

### Consumption:

1 litre for approx. 20 m<sup>2</sup> per application = 50 ml/m<sup>2</sup> per application

### Drying/Room climate:

12-24 hours drying time refers to normal temperature-conditions of +20°C and relative air-humidity of 55%.

### Storage:

Keep dry and cool (store or transport not under +6°C). Shelf life in unopened original container for several years under conditions of appropriate storage. Keep opened containers tightly closed and work up soon. Protect from cold.

### Cautions:

Keep IRSA Exotic-Wood-Oil out of the reach of children. Do not empty this product into canalization, any stretches of water or soiled ground. In case of eye- or skin-contact rinse off immediately with clear water. Only empty couples for recycling. Disposal of dried rests only at special waste collection points.

**Safety data sheets for professional users available on request. In exposure to chemicals regard the usual precautions. WGK 1, Giscode Ö60**